

G-01-09
 QQ-A-250/4E
 AMENDMENT-1
 October 22, 1974

FEDERAL SPECIFICATION

ALUMINUM ALLOY 2024, PLATE AND SHEET

This amendment, which forms part of Federal Specification QQ-A-250/4E, dated January 18, 1971, was approved by Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

Page 3

Table II - Mechanical properties, for "~~Temper T3 4/~~" delete in its entirety and substitute:

"Temper	Width	Thickness	Tensile strength, minimum	Yield strength at 0.2 percent offset or at extension indicated		Elongation in 2 in. or 4 times D ₁ /2/. minimum
				Minimum	Extension under load	
	Inches	Inches	P.s.i.	P.s.i.	Inch/Inch	Percent
T3 4/	All	0.008 thru 0.009	63,000	42,000	0.0060	10
	All	.010 thru .020	63,000	42,000	.0060	12
	All	.021 thru .128	63,000	42,000	.0060	15
	All	.129 thru .249	64,000	42,000	.0060	15"

MILITARY CUSTODIANS:

Army - MR
 Navy - AS
 Air Force - 11

Preparing activity:

Navy - AS
 (Project 9535-0230)

Review activities:

Army - ME, MU, WC, EL
 Navy - EC, SH
 Air Force - 84

User activities:

Army - ME
 Navy - MC, OS

FBO 9535